



EMSL Analytical, Inc.

29 North Plains Highway, Unit # 4 Wallingford, CT 06492

Tel/Fax: (203) 284-5948 / (203) 284-5978

<http://www.EMSL.com> / wallingfordlab@emsl.com

EMSL Order: 241900874

Customer ID: TIGH62

Customer PO:

Project ID:

Attention: Kevin McCarthy

Tighe & Bond

213 Court Street

Suite 1100

Middletown, CT 06457

Project: 28-2087-0330/ STARK ELEMENTARY SCHOOL MOLD ABATEMENT, 398 GLENBROOK ROAD, STAMFORD, CONNECTICUT

Phone: (860) 704-4760

Fax: (860) 704-4775

Received Date: 02/21/2019 3:15 PM

Analysis Date: 02/22/2019

Collected Date: 02/22/2019

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
0221BS01A 241900874-0001	1st floor room 170 - paper insulation	White Fibrous Homogeneous	85% Cellulose	15% Non-fibrous (Other)	None Detected
0221BS01B 241900874-0002	1st floor room 170 - paper insulation	Tan/Silver Fibrous Homogeneous	70% Cellulose	30% Non-fibrous (Other)	None Detected
0221BS02A 241900874-0003	1st floor room 170 - mudded elbow	Gray Fibrous Homogeneous	95% Min. Wool	5% Non-fibrous (Other)	None Detected
0221BS02B 241900874-0004	1st floor room 170 - mudded elbow	Gray Fibrous Homogeneous	85% Min. Wool	15% Non-fibrous (Other)	None Detected
0221BS02C 241900874-0005	1st floor room 170 - mudded elbow	Gray Fibrous Homogeneous	80% Min. Wool	20% Non-fibrous (Other)	None Detected
0221BS03A 241900874-0006	1st floor room 170 - yellow fiberglass	Yellow Fibrous Homogeneous	95% Min. Wool	5% Non-fibrous (Other)	None Detected
0221BS03B 241900874-0007	1st floor room 170 - yellow fiberglass	Yellow Fibrous Homogeneous	95% Min. Wool	5% Non-fibrous (Other)	None Detected
0221BS04A 241900874-0008	1st floor room 170 - black tar	Brown/Black Fibrous Homogeneous	60% Min. Wool	40% Non-fibrous (Other)	None Detected
0221BS04B 241900874-0009	1st floor room 170 - black tar	Brown Fibrous Homogeneous	50% Min. Wool	50% Non-fibrous (Other)	None Detected

Analyst(s)

Almedina Hodzic (5)

Leslie Tetrick (4)

Almedina Hodzic

Almedina Hodzic, Asbestos Laboratory Manager
or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. The above analyses were performed in general compliance with Appendix E to Subpart E of 40 CFR (previously EPA 600/M4-82-020 "Interim Method"), but augmented with procedures outlined in the 1993 ("final") version of the method. This report relates only to the samples reported above, and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. All samples received in acceptable condition unless otherwise noted. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. EMSL recommends gravimetric reduction for all non-friable organically bound materials prior to analysis. Estimation of uncertainty is available on request.

Samples analyzed by EMSL Analytical, Inc. Wallingford, CT NVLAP Lab Code 200700-0.

Initial report from: 02/22/2019 15:13:11